



ULTRATECH
INTERNATIONAL, INC.

Ultra-Gravel Bag[®]

Specifications

Part No. 9782 (11" x 48"), 9783 (11" x 96"), 9784 (11" x 250 yards - 2-pack)

Property	Test Method	Woven (Typical:)
Fabric Weight	ASTM D-5261	3.74 oz./sq./yd.
Grab Tensile (MD/TD)	ASTM D-4632	184/160 lbs.
Trapezoid Tear (MD/TD)	ASTM D-4533	99/67 lbs.
Puncture	ASTM D-6241	558 lbs.
Mullen Burst Test	ASTM D 3786	382 lbs.
Seam Strength	ASTM D4884	358(ppi)
Apparent Opening Size	ASTM D-4751	30 US Sieve (0.425mm).
Permittivity	ASTM D-4491	2.7 sec ⁻¹
Permeability	ASTM D-4491	0.14 cm/sec
UV Resistance (500hrs)	ASTM D-4355	>80%
Material		High Density Polyethylene (HDPE)
Diameter*		5.8 inches

**For 9782 and 9784 only. Assumes bag is completely stuffed and has a circular profile.*